

Mechanical Properties

	Grade	UTS	YST	% Elongation (min)	
		MPa, (min)	MPa, (min)	≤ 25.4 mm	> 25.4 mm
a	Yst 210	330	210	12	20
b	Yst 240	410	240	10	15
c	Yst 310	450	310	8	10